

E-212 Kitchlu Nagar, Ludhiana - 141001 ,

Fax : +91 161 5039900

Mob. +91-9878997708 | Toll Free No.1800-180-2999 (Extn.2238 )

Visit us at <http://www.tridentindia.com>

| TRIDENT LIMITED              |                             |         |                                  |             |             |             |            |
|------------------------------|-----------------------------|---------|----------------------------------|-------------|-------------|-------------|------------|
| QUALITY ASSURANCE DEPARTMENT |                             |         |                                  |             |             |             |            |
| NOMENCLATURE                 |                             |         | SUPER LINE (AS) 90 % Bright, NSS |             |             |             |            |
| PRODUCT SPECIFICATIONS       |                             |         |                                  |             |             |             |            |
| S.NO.                        | PARTICULARS                 | UOM     | 54/56 GSM                        | 58/60 GSM   | 68/70 GSM   | 78/80 GSM   |            |
| 1                            | Substance                   | $g/m^2$ | $\pm 2.5\%$                      | $\pm 2.5\%$ | $\pm 2.5\%$ | $\pm 2.5\%$ |            |
| 2                            | Bulk                        | cc/g    | 1.27 min                         | 1.27 min    | 1.27 min    | 1.27 min    |            |
| 3                            | Breaking Length             | MD      | meter                            | 4200 min    | 4200 min    | 4200 min    | 4200 min   |
|                              |                             | CD      | meter                            | 2100 min    | 2100 min    | 2100 min    | 2100 min   |
| 4                            | Tear Factor                 | MD      | -                                | 40 min      | 40 min      | 40 min      | 40 min     |
|                              |                             | CD      | -                                | 42 min      | 42 min      | 42 min      | 42 min     |
| 5                            | Smoothness ( Bendtsen )     | I Side  | ml/min                           | 180 max     | 180 max     | 180 max     | 180 max    |
|                              |                             | II Side | ml/min                           | 260 max     | 260 max     | 260 max     | 260 max    |
| 6                            | Cobb-60                     | TS      | $g/m^2$                          | $25 \pm 2$  | $25 \pm 2$  | $25 \pm 2$  | $25 \pm 2$ |
|                              |                             | WS      | $g/m^2$                          | $26 \pm 2$  | $26 \pm 2$  | $26 \pm 2$  | $26 \pm 2$ |
| 7                            | Brightness L&W Elrepho      |         | % ISO                            | 89 min      | 89 min      | 89 min      | 89 min     |
| 8                            | Opacity (Print) L&W Elrepho |         | %                                | 83 min      | 86 min      | 88 min      | 90 min     |
| 9                            | Passed Wax Pick No.         |         | no.                              | 12A         | 12A         | 12A         | 12A        |

The above Specifications have been posted on request of "SHREENATH PAPER PRODUCTS PVT. LTD."