

E-212 Kitchlu Nagar, Ludhiana - 141001 ,

Fax : +91 161 5039900

Mob. +91-9878997708 | Toll Free No.1800-180-2999 (Extn.2238)

Visit us at <http://www.tridentindia.com>

TRIDENT LIMITED						
RESEARCH & DEVELOPMENT DEPARTMENT						
NOMENCLATURE			PLATINUM LINE SS			
PRODUCT SPECIFICATIONS						
S.NO.	PROPERTIES		UOM	64 GSM	68/70 GSM	78/80 GSM
1	Substance		g/m ²	± 2.5%	± 2.5%	± 2.5%
2	Bulk		cc/g	1.22 min	1.22 min	1.22 min
3	Breaking Length	MD	meter	4800 min	4800 min	4800 min
		CD	meter	2400 min	2400 min	2400 min
4	Tear Factor	MD	-	43 min	43 min	43 min
		CD	-	45 min	45 min	45 min
5	Smoothness (Bendtsen)	I Side	ml/min	190 max	190 max	190 max
		II Side	ml/min	110 max	110 max	110 max
6	Cobb ₆₀	I Side	g/m ²	26 ± 2	26 ± 2	26 ± 2
		II Side	g/m ²	25 ± 2	25 ± 2	25 ± 2
7	Brightness L & W Elrepho		% ISO	90 min	90 min	90 min
8	Opacity (Print) L& W Elrepho		%	87 min	89 min	91 min
9	Scattering Coefficient		m ² / kg	43 min	43 min	43 min
10	Passed Wax Pick No.		no.	14A	14A	14A

The above Specifications have been posted on request of “SHREENATH PAPER PRODUCTS PVT. LTD.”