

E-212 Kitchlu Nagar, Ludhiana - 141001 ,

Fax : +91 161 5039900

Mob. +91-9878997708 | Toll Free No.1800-180-2999 (Extn.2238)

Visit us at <http://www.tridentindia.com>

TRIDENT LIMITED				
RESEARCH & DEVELOPMENT DEPARTMENT				
NOMENCLATURE			ROYAL TOUCH 80 GSM	
PRODUCT SPECIFICATIONS				
S.No.	Properties	UOM	80 GSM	
1	Substance (A)	g/m ²	80 ± 2.5%	
2	Thickness	micron	107 min	
3	Bulk	cc/g	1.34 min	
4	Breaking Length	MD	meter	4800 min
		CD	meter	2400 min
5	Tear Factor	MD	-	45 min
		CD	-	48 min
6	Smoothness (Bendtsen)	I Side	ml/min	350 ± 100
		II Side	ml/min	200 ± 100
7	Cobb ₆₀	I Side	g/m ²	26 ± 2
		II Side	g/m ²	25 ± 2
8	ISO Brightness , L & W Elrepho		% ISO	89 min
9	CIE Whiteness , L&W Elrepho		%	155 min
10	Opacity (Print) L& W Elrepho		%	92 min
11	Stiffness (Taber)	MD	Taber	2.1 min
		CD	Taber	1.0 min
12	Passed Wax Pick No.		no.	14 A

The above Specifications have been posted on request of “SHREENATH PAPER PRODUCTS PVT. LTD.”